Optimization of Cr(VI) Photocatalytic Reduction by UV/TiO₂: Influence of Inorganic and Organic Species and Kinetic Study

Amir Azizi^a, Javad Saien^b

^aDepartment of Chemistry, Faculty of science, Arak University, Arak, 38156-8-8138, Iran. ^bDepartment of Applied Chemistry, Bu-Ali Sina University, Hamedan, 65174, Iran.

*Correspondence should be addressed to Dr. Amir Azizi, Email: a-azizi@araku.ac.ir

A-R-T-I-C-L-EI-N-F-O

Article Notes: Received: Jan12, 2018 Received in revised form: Apr 23, 2018 Accepted: Apr 28, 2018 Available Online: May 1, 2018

Keywords:

Photocatalytic reduction, Hexavalent chromium, Hole scavenger, Kinetic, Energy consumption, Iran.

A-B-S-T-R-A-C-T

Background & Aims of the Study: Chromium is widely detected in surface waters and underground waters, which usually appear as Cr(VI), and Cr(III), at sites associated with industrial activities. Cr(VI), in effluent streams with a high level of mobility and notorious mutagenic and carcinogenic toxicity; thus Cr(III) does not have much mobility in soil. So, converting it into less harmful species could be beneficial.

Materials & Methods: Cr(VI) photocatalytic reduction in aqueous media was analyzed using desperately low dosages of nanoparticles of commercial titania. A directly imposed irradiation photoreactor equipped with a supersonic source was applied. The optimization of the reduction process was done using the central composite design (CCD) experimental. The residual concentration of Cr(VI) ion was determined by colorimetrically method. In addition, the impact of other factors, including water matrix and hole scavengers, also reduction kinetics were studied.

Results: A quadratic equation for reduction efficiency was proposed, and the adequacy of it was evaluated by a variety of statistical methods. A maximum of 80.6% reduction in aqueous samples containing an initial concentration of Cr(VI) within the investigated optimum operating condition (TiO₂ dose of 33 mg/L; pH of 2.5, T=35 °C and t=120 min) was obtained. Results indicate that UV irradiation alone is an acceptable method for Cr(VI) reduction maybe due to H₂O₂ photolytic generation. The results show Cr(VI) photoreduction was greatly enhanced by about 88.2% when NO₃⁻ was used in comparison with SO₄²⁻ anion. The photoreduction enhancements with the scavengers are appeared in the following order ethylene glycol > formic acid > citric acid with relevant. Maximum reduction of 96.5% for Cr(VI) was obtained in the presence of ethylene glycol hole scavenger. The results indicated that the process rate can be presented with a pseudo-first-order kinetic model.

Conclusion: The results showed, the CCD design was approximately adequate in Cr(VI) reduction, so it can be a suitable option for water quality improvement. The addition of inorganic or organic species can act as scavenging hydroxyl radicals- which are photo-generated- and valanceband holes that are on the photocatalysts of the semiconductor, and consistently, enhance the photocatalytic reduction of Cr(VI) ion.

Please cite this article as: Azizi A, Saien J. Optimization of Cr(VI) Photocatalytic Reduction by UV/TiO₂: Influence of Inorganic and Organic Species and Kinetic Study. Arch Hyg Sci 2018;7(2):81-90.

Background

Heavy metal ions are commonly occurring as toxic metals in natural ecosystems due to the effluent of electroplating, electronic, tanning industries and etc. (1,2). These ions are assimilated, stored, and concentrated by organisms that are exposed to them (3,4). In aquatic environments, one common pollutant metal ion is chromium that usually appears as Cr(VI) and Cr(III) (5). Though Cr(VI) has high toxicity; only a slight toxicity have been reported for Cr(III), and it is easily precipitated at neutral and alkaline pH (6). So, the reduction of Cr(VI) to Cr(III), which is less harmful would be beneficial.

Precipitation, ion exchange, adsorption, electrolysis, membrane processes and photocatalysis are common methods have been proposed for the treatment of Cr(VI) ion in wastewater (7-11). In the photocatalysis process, mostly titanium dioxide is used, because it's really active photocatalytically, and it's inexpensive, as well (12). Formation of electron-hole pairs $(e_{CB}^{-}-h_{VB}^{+})$ on the catalyst surface when a photon with enough energy is used to overcome the band gaps of titania is the main step in this process. On the catalyst surface when is used a photon with enough energy is used to overcome the band gaps of titania is the main step in this process. It is clear that the band gap of TiO_2 is around 3.2 eV with the conduction band -0.3 eV and the valence band of +2.9 eV at pH 5.6 (13). Cr(VI) ion which has a reduction potential less negative than -0.3 eV would be reduced by generated electrons of TiO₂; while water and organic pollutants are oxidized by the holes either directly or indirectly.

Photocatalytic reduction of Cr(VI) ion has been investigated several times; The existing researches in the literature, on the reduction of chromium, are about the application of OFAT in very high concentrations of TiO_2 (on the level 103 mg/L or above) (14,15). In the this research, photo-reduction was conducted using small amounts of TiO₂ particles, and to better evaluate the Cr(VI) reduction efficiency, the RSM methodology based on CCD was used. dosage catalyst loading practically Low resolves separation and regeneration problems. TiO₂ initial dosage and three important operational variables including pH, temperature and time were contemplated to study the effect of these on the reduction efficiency (RE) of chromium and to evaluate the optimum conditions. In order to realize the impact of other factors such as inorganic anions and hole scavengers, a number of experiments were designed and performed on the Cr(VI) reduction efficiency. Finally, to put this into practice, the process performance is evaluated from the aspect of reactions kinetics, process efficiency and energy consumption.

Aims of this study:

The aims in this research were to demonstrate the successful application of CCD using a very low dosage of TiO_2 in a sono-photo reactor as a suitable reactor; and the impact of inorganic and organic species on the photocatalytic reduction efficiency.

Materials & Methods

Chemicals

All the used chemicals used in this research were of analytical grade (purity >99.5%). TiO₂ (P-25, purity >99.5%, 75% anatase, 25% rutile) was obtained from Plasma Chem. with 50 m^2/g and 21 nm specific surface area and mean particle size, respectively. The other chemicals including potassium dichromate, 1.5diphenylcarbohydrazide (DPC), hydrochloric acid, sodium nitrate, sodium sulfate, sodium hydroxide, ethylene glycol, formic acid and citric acid were purchased from Merck Company. Deionized water (conductivity less than 0.08 μ S/cm) was utilized for the solutions. Procedure and analytical method

Photocatalytic experiments were conducted in a cylindrical sono-photo reactor made of glossy stainless steel with dimensions in 90 mm diameter and 200 mm in height (16). The light source was A 250 W mercury bulb with a maximum emission wavelength of 365 nm which was centrally-located; and it irradiated the solution around, directly. An ultrasound source with the following features was placed at the outside bottom of the reactor for both fine mixing and the catalyst particle dispersion during each experiment (28 kHz, 60 W). A water-flow jacket was used to keep the temperature constant during the reaction.

Archives of Hygiene Sciences

Volume 7, Number 2, Spring 2018

The Cr(VI) solution was prepared with 5.0 mg/L of potassium dichromate in deionize water, after adjusting the pH with either dilute hydrochloric acid or sodium hydroxide. One liter of the solution was added to the reactor and then predetermined amounts of the TiO₂ particles were added also, mixing and temperature adjustment were completed, and the UV bulb was switched 2 milliliter samples were withdrawn periodically from the solution. The aqueous samples were centrifuged to separate the nano particles. The Cr(VI) ions residual concentration was determined colorimetrically with 1.5diphenylcarbohydrazide at λ_{max} =542 nm (17). By utilizing this methodology, the percentage of reduction efficiency (RE) was calculated with the following equation at any moment:

$$RE = \frac{[Cr(VI)]_{\circ} - [Cr(VI)]_{t}}{[Cr(VI)]_{\circ}} \times 100$$
(1)

 $[Cr(VI)]_{\circ}$ and $[Cr(VI)]_{\circ}$ in this equation represent the initial and time concentrations of Cr(VI), respectively.

Besides the variables applied in the RSM and optimization, the impact of other variables, like water matrix and hole scavengers, on Cr(VI) reduction were accounted for. To measure the impact of water matrix, the sample solutions containing determined amounts of dissolved salts such as NaNO₃ and Na₂SO₄ were used. Also, the batch tests were initiated by adding three hole scavengers to test the impact of them on the reduction efficiency. Furthermore, to investigate the reduction kinetics of Cr(VI), a power law kinetic model was applied, in optimum conditions. Also, the consumption of electrical energy as a practical and economic parameter was evaluated.

Experimental design and statistical analysis In the current study, the central component design (CCD), which is the most conventional type of response surface methodology (RSM), was employed to optimization of photocatalytic Cr(VI) reduction process. The required number of experiments (N) is obtained using $N = 2^{k} + 2k + C_{0}$ where "k" is the parameters number and C_0 is the replicate number of the central point, respectively (18). The variable parameters were the solution pH, TiO₂ dosage, time and temperature. The aggregate number of required experimental runs was 30. The quadratic equation determines the best mathematical relationship between variable the adsorption parameters and process efficiency:

$$y_{\text{Pred}} = \beta_0 + \sum_{i}^{k} \beta_i x_i + \sum_{i}^{k} \beta_{ii} x_i^2 + \sum_{i}^{k-1} \sum_{j=i+1}^{k} \beta_{ij} x_i x_j + \varepsilon \quad (2)$$

where y stands for the forecasted response, $\beta 0$ the constant, Bi the linear, Bii the quadratic and βij the interaction coefficients and "xi, xj" are the impactful process variables, m is the number of variables and ε is the residual error. Design Expert 8.0 software was applied to design experiments the and graphical investigation of the obtained data. The dependability of the defined model was explained via analysis of variance (ANOVA) and R^2 coefficient. The experimental ranges of the coefficients concerning Cr(VI) reduction are summarized in Table 1.

	Levels and ranges						
Variables	-α	(-1)	(0)	(+1)	+α		
Solution pH, X_{nH}	1.8	2.5	4.0	5.5	6.1		
$[TiO_2] dosage \qquad (mg/L),$	1.0	8.0	25.0	42.0	49.0		
Temperature (°C), X_T	16.7	20.0	28.0	36.0	39.3		
Reaction time (min), X_t	47.6	60.0	90.0	120.0	132.4		

Table 1) Ranges and levels of the experimental variables

Archives of Hygiene Sciences

Volume 7, Number 2, Spring 2018

Results

(3)

The Mathematical Modeling

The outcomes of using CCD model to Cr(VI) ion reduction show that RE ranges from 8.9 to 82.2% invarious conditions. In order to obtain the right data, the numbers were fitted experimentally to come up with the best removal efficiency equation. A quadratic equation was developed (Eq.3) which correlates with reduction efficiency as an initial pH function, TiO₂ dosage, temperature and time

 $RE = 28.36 - 12.06x_{\text{pH}} + 4.34x_{\text{TiO}_2} + 10.96x_T +$ $7.63x_t - 4.45x_{\text{pH}}x_T - 3.61x_{\text{pH}}x_t + 3.61x_tx_T +$ $4.68x_{\text{pH}}^2 - 4.61x_{\text{TiO}_2}^2 + 3.07x_T^2 + 2.07x_t^2$

The analysis of variance (ANOVA) was performed for the quadratic developed model.

• Optimization of Cr(VI) Photocatalytic Reduction by...

Results in Table 2 demonstrate that the model of regression was determined to be (0.993), which demonstrates that 99.3% of the variables affects the determination of the reduction efficiency of Cr(VI). The amount of the Adj-R² (0.988) is also very adjacent to the corresponding R² value. Moreover, the value of pred-R² which is 0.9758 seems to demonstrate good agreement with that of Adj-R². The amount of prob>F which is less than 0.0001 and the 219.07 F-value imply that this equation is satisfactory. The latter criterion is obtained from mean square model divided by the residual mean square (18).

Also, the F-value which is lack-of-fit (an experiment to compare the variance which is lack-of-fit with the pure error variance) and is 2.35, implies that the lack-of-fit value is not significantly related to the pure error.

Table 2) Analysis of variance	(ANOVA) for $Cr(VI)$ reductions
I ADIC 2/ AHAIVSIS UL VALIANC	E (ANOVA) IOI CI(VI) IEUUCIONA

Source o variations	f Sum of squares	Degrees of freedom	Mean square	F-Value	Prob>F
Regression	8116.0	11	737.8	219.1	< 0.0001
Residual	60.6	18	3.4		
Lack of Fit	52.1	13	4.0	2.3	< 0.1773
Pure Error	8.5	5	1.7		
Cor Total	8176.6	29			

 ${}^{a}R^{2}$ = 0.993, adj- R^{2} = 0.988, pred- R^{2} = 0.976

An adequacy check of the obtained applied model is essential in the experimental analysis. A suitable model can ensure an excellent estimation of real conditions. In Figure 1, the predicted values for Cr(VI) reduction of the model have been plotted versus the \mathbf{R}^2 experimentally determined data. The determined coefficient was calculated as 0.992 for Cr(VI) reduction, indicating a good agreement between the predicted data and the experimental data.





Archives of Hygiene Sciences Volume 7, Number 2, Spring 2018

• Optimization of Cr(VI) Photocatalytic Reduction by...

Discussion

Evaluating Results and Chemical Aspects The photocatalytic Cr(VI) reduction in the Cr(VI)/TiO₂ system was studied with 5 mg/L initial Cr(VI) concentration, TiO₂ loading of (8-50) mg/L, solution pH between 2.5 and 6.5 and temperature within the conventional range of 20 to 40 °C. As the photocatalyst loading increases to 33 mg/L, the efficiency of Cr(VI) reduction increases When the catalyst amount was further increased, a negative effect was observed due to the blockage of light caused by excessive catalyst loading (19). At acidic pHs, dichromate (Cr_2O7_2) , hydrogen chromate $(HCrO_4)$, and the chromate $(CrO_4^{2^{-}})$ anion species are adsorbed onto the positively charged catalyst surface (20). It has been pointed that the redox potential of Cr(VI)/Cr(III) pair decreases by 98 mV per pH unit (21). Therefore, the presence of acid sites on catalyst surface may favor Cr(VI) reduction. Results also show that Cr(VI) photocatalytic reduction rises with anv temperature increase, from 20 to 36 °C and then remains almost constant, perhaps due to disfavorable effect of temperature on adsorption; however, a contradicting variation was relevant with pH. Furthermore results show that RE increases as the reaction time increases; however, the variation is more respondent at low pHs and high temperatures, exhibiting a more pleasant reaction. After screening the factors and their interactions, a maximum of 81.5% Cr(VI) reduction is predictable with titania dosage of about 33 mg/L, and other conditions including pH=2.5, T=35 °C and t=120 min. The confirmatory experiment run an efficiency of 80.6% of Cr(VI) under these conditions (Figure 2). This closeness confirms the validity of the model reliability. It was also identified that the Cr(VI)photocatalytic reduction obeys the first order kinetic model. The rate constant of Cr(VI) photocatalytic reduction at the mentioned conditions was $1.37 \times 10^{-2} \text{ min}^{-1}$.





To investigate the contributing branches in the reduction; experiments were performed under optimum conditions either in the presence (photocatalysis) or in the absence (photolysis) of titania. The trend of Cr(VI) concentration variations during the processes time is depicted in Figure 3. As shown in the inset figure, obtained REs at two typical moments, for both the cases. The RE exceeds 60% and 80% for the photocatalysis, and 41% and 62% for the photolysis, after 60 and 120 min, respectively. These indicate that photocatalysis operates more significantly and effectively than the photolysis alone; however, UV irradiation alone is an acceptable method. It can be said that the cavitation process occurs in the solution and during aqueous sonolysis, reactive radicals such as hydroxyl radicals, are generated and joined together to form H_2O_2 (22) which contributes in the reduction of Cr(VI) (Eq. 4) in the photolysis process (23).

 $2\text{HCrO}_4^- + 3\text{H}_2\text{O}_2 + 8\text{H}^+ \rightarrow 2\text{Cr(III)} + 3\text{O}_2 + 8\text{H}_2\text{O}$

(4)

The higher possibility of H₂O₂ photocatalytic production in an acidic condition (following equations) (24,25) can also be a reason for higher efficiencies in photocatalytic systems.

 $TiO_2 + hv \rightarrow$

$$\rightarrow e + h$$
 (5)

Archives of Hygiene Sciences

Volume 7, Number 2, Spring 2018

$$O_2 + e^- \rightarrow O_2^{\bullet-}$$
(6)
(H_2O \Leftrightarrow H^+ + OH^-) + h^+ \rightarrow H^+ + OH^{\bullet-}

$$\mathrm{H}^{+} + \mathrm{O_{2}}^{\bullet} \rightarrow \mathrm{HO_{2}}^{\bullet}$$

$$2HO_2^{\bullet} \rightarrow H_2O_2 + O_2 \tag{9}$$

(8)



Figure 3) The variation of Cr(VI) concentration versus time; the inset figure presents comparison of RE values after two different times for the photolysis and photocatalysis processes; pH=2.5, [TiO₂]=33 mg/L and T=35 °C

Effects of inorganic anions

 NO_3^- , Cl^- and SO_4^{2-} are inorganic anions that are usually present in chromium containing wastewaters. Inorganic anions can play the role scavenging photo-generated hydroxyl of radicals and holes- that are valance-band- on semiconductor the photocatalysts and consistently, enhance the metal ions photocatalytic reduction (26). To do so, the effect of NO_3^- and SO_4^{2-} anions on Cr(VI) reduction was studied with 50 mg/L nitrate or sulfate ion, which originated from NaNO₃ or Na₂SO₄ salt, being present in the solution; and the outcomes were illustrated in Figure 4. The addition of NO_3^- and SO_4^{2-} anions increased Cr(VI) photoreduction. The holes may be captured by sulfate or nitrate ions that cause the conduction-band electrons which are photo-

• Optimization of Cr(VI) Photocatalytic Reduction by...

promoted to become more available for Cr(VI) reduction, and inhibit the electron-hole recombination. The results show that Cr(VI) photoreduction was greatly enhanced (by about 88.2%) when NO₃⁻ was used. This can be explained that the NO₃⁻ ions in the solutions are capable in reducing Cr(VI) directly through nitrite reductant ions (NO₂⁻) produced from NO₃⁻ photolysis (27,28) (Eq. 11): $3NO_{2}^{-} + 2HCrO_{4}^{-} + 8H^{+} \rightarrow 2Cr(III) + 3NO_{3}^{-} + 5H_{2}O$

(11)

and indirectly by generating H_2O_2 molecules (29), which leads to rapid reduction of Cr(VI) according to (Eq. 4) (23).



Figure 4) Effect of water matrix on Cr(VI) photocatalytic reduction; pH=2.5, $[TiO_2]=33$ mg/L, $[NO_3^-]=[SO_4^{-2}]=50$ mg/L and T=35 °C

Effect of Hole Scavengers

In this study, to promote photocatalytic reduction of Cr(VI) ion, three conventional hole scavengers including formic acid, citric acid and ethylene glycol of 100 mg/L were used. Hole scavengers can be used to inhibit the recombination. In Figure 5 shows that the reduction of Cr(VI) ion is strengthened (compared with no scavenger case) with ethylene glycol and formic acid; however, there was no pronounced change with citric acid. The photoreduction enhancements with the scavengers appeared to be in the following order: ethylene glycol>formic acid>citric acid with relevant. Enhancement of the photocatalytic reduction, with ethylene glycol

Archives of Hygiene Sciences

Volume 7, Number 2, Spring 2018

•Optimization of Cr(VI) Photocatalytic Reduction by...

and formic acid presence, can be attributed mostly to the fact that ethylene glycol is first oxidized to oxalate ion $(C_2O_4^{2-})$ intermediate with irradiated TiO₂ in aqueous medium, and in turn, produces CO_2^{-} by further oxidation. This recent species which is also produced by formic acid, has the ability to reduce Cr(VI) and is converted to CO₂ itself. These reactions also inhibit the recombination (30,31). A simplified reduction mechanism with ethylene glycol scavenge function in Figure 6 is presented. In this research, by using 33 mg/L photocatalyst and in the presence of 50 mg/L nitrate anion about 88.2% RE was achieved without scavenger after 120 min and reached to 96.5% under the same conditions when ethylene glycol scavenger was used.



Figure 5) Effect of different hole scavengers (100 mg/L) on photoreduction of Cr(VI) ion; [TiO₂]=33 mg/L, pH=2.5, T=35 °C, [NO₃⁻]=50 mg/L and t=120 min



Figure 6) A simplified scheme of Cr(VI) photocatalytic reduction mechanism in the presence of ethylene glycol

Kinetic Study

For practical applications, the kinetic model was investigated under the found optimum conditions. The RE reaches to 96.5% in solution after 120 min.

For this purpose, a power law kinetic model (32) in the form (Eq. 12):

$$r = -\frac{d[Cr(VI)]}{dt} = k[Cr(VI)]^n$$
(12)

where r, [Cr(VI)], and k are the reaction rate, chromium concentration and rate constant, respectively and n is order reaction; to obtain kinetic parameters, the differential method of data analysis, based on the ions concentration variation versus time with 8 data points, was employed. Figure 7 presents the goodness of fitting with Eq. (12). The obtained kinetic parameters, in addition determination (\mathbb{R}^2) coefficient for Cr(VI) ion is presented in Table 3. The Cr(VI)/UV/TiO₂ process globally reveals a pseudo first order reaction.



Figure 7) Cr(VI) reduction efficiency versus time under conditions of pH=2.5, [TiO₂]=33 mg/L, [NO₃⁻] =50 mg/L, [Ethylene glycol]=100 mg/L, *T* =35 °C and *t*=120 min. Inset figure is the kinetic plot of the reactions under the same conditions

Archives of Hygiene Sciences

Volume 7, Number 2, Spring 2018

Table 3) Kinetic parameters of Cr(VI) reduction; pH=2.5, [TiO₂]=33 mg/L, [NO₃⁻]=50 mg/L, [Ethylene glycol]=100 mg/L, T=35 °C and t=120 min

Process	Order	Rate constant	R^2
Cr(VI)/UV/TiO ₂	0.95	$2.04 \times 10^{-2} (mg/L)^{0.05}/min$	0.930

Energy Consumption Evaluation

There are several vital factors in selecting a waste treatment technology, such as, effluent outlet quality, operation conditions, economics and etc., which all are important, this is while the economics is often dominant (33).Electrical energy consumption, EE, is the main parameter in the photochemical processes economic that can be obtained (in kWh/m³) for first order reactions which proposed by IUPAC, as (34) Eq: 13 (33). Eq. 13:

$$E_E = \frac{1000Pt}{60V \log\{[Cr(VI)]_{\circ}/[Cr(VI)]_{t}\}}$$
(13)

where P is the electric power (kW) of the photochemical system, V is the volume (L) of

the solution in the reactor, and t is the reaction time (min).

Accordingly, the electrical energy related to the reduction under conditions of 33 mg/L loading of TiO₂, initial pH 2.5, T=35 °C and in the presences of 50 and 100 mg/L nitrate anion and ethylene glycol, respectively after 120 min are 343.8 kWh/m³ for chromium. Considering the current electrical energy price in U.S. market as 0.06 US\$/kWh in 2017 (35), the electrical energy cost will be 20.6 US\$/m³ respectively. The EE values in this work in comparison with other reported processes (first order reactions and using nanoparticles for photocatalyst) are listed in Table 4.

1 able 4) Comparing the performance of different photocatalytic Cr(VI) reduction processes										
[Cr(VI)] _。 (mg/L)	[TiO ₂] (mg/L)	рН	<i>T</i> (°C)	UV dose (W/L)	time (min)	sacrificial reagent	RE (%)	E_E kWh/m ³	PE	Ref.
10	1000	2	25	7	300	-	70	66.9	1.05×10 ⁻³	(20)
150	2000	2.5	22	3000	60	formic acid	95	2305.9	2.06×10 ⁻⁵	(36)
150	2500	2.5	25	1000	180	-	80	4292.1	7.46×10 ⁻⁶	(37)
150	1000	3	25	1200	120	EDTA	90	2400.0	3.74×10 ⁻⁵	(38)
5	33	2.5	35	250	120	-		608.7	4.01×10 ⁻³	This work
5	33	2.5	35	250	120	Ethylene glycol	96.5	343.8	8.50×10 ⁻³	This work

Table 4) Comparing the performance of different photocatalytic Cr(VI) reduction processe

Assessment of Process Performance

A valid criterion in this regard can be proposed, as process efficiency (PE), when RE is determined to unit EE and unit photocatalyst amount (32), presented in the practical equation of (Eq. 14):

$$PE = \frac{RE}{E_E \times [\text{TiO}_2]} \tag{14}$$

where E_E and $[TiO_2]$ are consumption the electrical energy in kWh/m³ and the catalyst

loading in mg/L. Generally, PE reflects to the efficiency achievement with respect to the level of consumption energy as well as the used catalyst amount. Accordingly, the effect of temperature and the reaction progress with time are contributed in the PE via EE parameter. The PE value in the present work (under mentioned conditions) is significantly higher than relevant other reported processes (Table 4). This matter together with the significant achieved efficiency, confirm the high performance of the used process.

Archives of Hygiene Sciences	Volume 7, Number 2, Spring 2018
© 2018 Publisher: Research Center for Environmental Pollutants,	Qom University of Medical Sciences. All rights reserved.

Conclusion

Potocatalytic reduction of Cr(VI) to Cr(III) in the presence of titanium dioxide nanoparticles was studied with solution pH, dose of TiO₂, temperature and reaction time factors. The most important results: (i) Application of a central composite experimental design helped in finding a maximum of about 81% reduction in solutions containing 5 mg/L of Cr(VI), under operating conditions of pH of 2.5; titania dose of only 33 mg/L and temperature of 35 °C during about 120 min of treatment process; (ii) The results show Cr(VI) photoreduction were greatly enhanced when NO_3^- was used in comparison with the addition of SO_4^{2-} anions; (iii) The activity of the used hole scavengers were appeared in the order of ethylene glycol>formic acid>citric acid; (iv) Appling the pertinent conditions, RE of 96.5% were achieved; (v) Pseudo first order reactions for Cr(VI) photocatalytic reduction is relevant; (vi) Electrical energy consumption analysis showed a relatively low required energy for the this study in comparison with a previous work; and (vii) Based on different criteria including economic parameters, the significant preference of the used process was demonstrated.

Footnotes

Acknowledgement:

The authors wish to acknowledge the university authorities for providing the financial support to carry out this work.

Conflict of Interest:

The Authors have no conflict of interest.

Furthermore, authors declare that a part of the results in this study has been presented at the International Conference Engineering and applied sciences which were held in Dubai at 2016.

References

1. Xu H, Liu Y, Tay J. Effect of pH on nickel biosorption by aerobic granular sludge. Bioresource Technology 2006;97(3):359–363.

2. Yoon J, Shim E, Joo H. Photocatalytic reduction of hexavalent chromium (Cr(VI)) using rotating TiO_2 mesh. Korean J Chem Eng 2009;26(5):1296–1300.

3. Gupta V, Ali I. Removal of cadmium and nickel from wastewater using bagasse fly ash-a sugar industry waste. Water Res 2003; 37(16):4038–4044.

4. Gupta V, Jain C, Ali I, Sharma M, Saini V. Removal of lead and chromium from wastewater using bagasse fly ash-a sugar industry waste. J. Colloid Interface Sci 2004;271(2):321–328.

5. Chen D, Ray A. Removal of toxic metal ions from wastewater by semiconductor photocatalysis. Chem Eng Sci 2001; 56 (4): 1561–1570.

6. Sibonia M, Samadi M,, Yangc J, Leed S. Photocatalytic removal of Cr(VI) and Ni(II) by UV/TiO₂: kinetic study. Desalination Water Treat 2012; 40 (1-3): 77–83.

7. Caliman A, Teodosiu C, Balasanian I. Applications of heterogeneous photocatalysis for industrial wastewater treatment. Environ Eng Manag J 2002; 1 (2): 187–196.

8. Lacour S, Bollinger C, Serpaud B, Chantron D, Arcos R. Removal of heavy metals in industrial wastewaters by ion-exchanger grafted textiles. Anal Chim Acta 2001; 428: 121–132.

9. Malkoc E, Nuhoglu Y. Removal of Ni(II) ions from aqueous solutions using waste of tea factory: Adsorption on a fixed-bed column. J Hazard Mater 2006; 135 (1-3): 328–336.

10. World Health Organization, Guidelines for Drinking Water Quality, 3rd ed. Geneva, Switzerland; 2006. p. 54. 11. Wu W, Peng J. Linear control of electrochemical tubular reactor system—Removal of Cr(VI) from wastewaters. J Taiwan Inst Chem Eng 2011; 42 (3): 498-505.

12. Bhatkhande S, Pangarkar G, Beenackers A. Photocatalytic degradation for environmental applications-a review. J Chem Technol Biotechnol 2001; 77 (1): 102–116.

13. Blake M, Webb J, Turchi C, Magrini K. Kinetic and mechanistic overview of titania photocatalyzed oxidation reactions in aqueous solution. Sol Energy Mater Sol Cells 1991; 24 (1-4): 584–593.

14. Khalil L, Mourad W, Rophael M. Photocatalytic reduction of environmental pollutant Cr(VI) over some semiconductors under UV/visible light illumination. Appl Catal B 1998; 17: 267–273.

15. Ku Y, Jung I. Photocatalytic reduction of Cr(VI) in aqueous solutions by UV irradiation with the presence of titanium dioxide. Water Res 2001; 35 (1): 135–142.

16. Saien J, Delavari H, Solymani A. Sono-assisted photocatalytic degradation of styrene-acrylic acid copolymer in aqueous media with nano titania particles

Archives of Hygiene Sciences

Volume 7, Number 2, Spring 2018

• Optimization of Cr(VI) Photocatalytic Reduction by ...

and kinetic studies. J Hazard Mater 2010; 177 (1-3): 1031–1039.

17. Editorial board of environment protection bureau of China, Monitoring and Determination Methods for Water and Wastewater. 4th ed., Beijing, China Environmental Science press; 2002.

18. Sakkas V, Islam M, Stalikas C, Albanis T. Photocatalytic degradation using design of experiments: Areview and example of the congo red degradation. J Hazard Mater 2010; 175 (1-3): 33–44.

19. Saien J, Nejati H. Enhanced photocatalytic degradation of pollutants in petroleum refinery wastewater under mild conditions, J Hazard Mater 2007; 148 (1-2): 491–495.

20. Ku Y, Jung I. Photocatalytic reduction of Cr(VI) in aqueous solutions by UV irradiation with the presence of titanium dioxide. Water Res 2001; 35 (1): 135–42.

21. Gratzel M., Energy resources through photochemistry and catalysis, Academic Press, New York; 1983.

22. Joseph C, Gianluca L. Sonophotocatalysis in advanced oxidation process: a short review. Ultrason Sonochem 2009; 16 (5): 583–589.

23. Pettine M, Campanella L, Millero F. Reduction of hexavalent chromium by H2O2 in acidic solutions. Environ Sci Technol 2002; 36 (5): 901–907

24. Wang S, Chen C, Tzou Y. A mechanism study of light-induced Cr(VI) reduction in acidic solution. J Hazard Mater 2009; 164 (1): 223–228.

25. Kyung H, Lee J, Choi W. Simultaneous and synergistic convwesion of dyes and heavy metal ions in aqueous TiO2 suspensions under visible-light illumination. Environ Sci Technol 2005; 39 (7): 2376–2382.

26. Burns R, Crittenden J, Hand D, Selzer V, Sutter L, Salman S. Effect of inorganic ions in the heterogenous photocatalysis of trichloroethene. J Environ Eng 1999; 125 (1): 77–85.

27. Hsu C, Wang S, Tzou Y. Photocatalytic reduction of Cr(VI) in the presence of NO3 – and Cl– electrolytes as influenced by Fe(III). Environ Sci Technol 2007; 41(22): 7907–7914.

28. Penpolcharoen M, Amal R, Brungs M. Degradation of sucrose and nitrate over titania coated nano-hematite photo-catalysts. J Nanopart Res 2001; 3: 289–302.

29. Mack J, Bolton J. Photochemistry of nitrite and nitrate in aqueous solution: a review. J Photochem Photobio 1999; 128 (1-3): 1–13.

30. Forouzan F, Richards T, Bard A. Photoinduced reaction at TiO2 particles. photodeposition from Ni(II) solutions with oxalate. J Phys Chem A 1996; 100 (46): 18123–18127.

31. Wang X, Pehkonen S, Ray A. Removal of aqueous Cr(VI) by a combination of photocatalytic reduction and coprecipitation, Ind Eng Chem. Res 2004; 43 (7): 1665–1672.

32. Saien J, Azizi A, Soleymani A. Optimized photocatalytic conversion of Ni(II) ions with very low titania nanoparticles at different temperatures; kinetics and energy consumption. Sep Purif Technol 2014; 134: 187-195.

33. Khataee A, Safarpour M, Zarei M, Aber S. Combined heterogeneous and homogeneous photodegradation of a dye using immobilized TiO2 nanophotocatalyst and modified graphite electrode with carbon nanotubes. J Mol Catal A 2012; (363–364): 58–68.

34. Bolton J, Bircher K, Tumas W, Tolman C. Figuresof-merit for the technical development and application of advanced oxidation technologies for both electric and solar-driven systems. Pure Appl Chem 2001; 73 (4): 627–637.

35. http://www.eia.doe.gov (US Government Energy Information Administration, Independent Statistics and Analysis); 2017.

36. Wang X, Pehkonen S, Ray A. Removal of aqueous Cr(VI) by a combination of photocatalytic reduction and coprecipitation. Ind Eng Chem Res 2004; 43(7): 1665–1672.

37. Jiang F, Zheng Z, Xu Z, Zheng S, Guo Z, Chen L. Aqueous Cr(VI) photo-reduction catalyzed by TiO2 and sulfated TiO2. J Hazard Mater 2006; 134(1-3): 94–103.

38. Siemon U, Bahnemann D, Testa J, Rodriguez D, Litter M, Bruno N. Heterogeneous photocatalytic reactions comparing TiO2 and Pt/TiO2. J Photochem Photobiol A 2002; 148 (1-3): 247–55.

Archives of Hygiene Sciences

Volume 7, Number 2, Spring 2018